

PATENT CLAIMS

1. Moulding composition for the production of sanitary-ware components, comprising a methyl-methacrylate-based syrup and from 50 to 85%, expressed in terms of the moulding composition, of an inorganic filler, characterised in that the moulding composition furthermore comprises elastomer particles or elastomer particle aggregates having a particle size smaller than 100 μm in an amount in the range of 5 % by weight to < 20 % by weight, expressed in terms of the mass of the syrup.

10 2. Moulding composition according to Claim 1, characterised in that the syrup comprises PMMA with a molecular weight (M_w) of from 50,000 to 250,000 in an amount of up to 20 % by weight, expressed in terms of the mass of the syrup.

15 3. Moulding composition according to Claim 1 ~~or 2~~, characterised in that it contains a proportion of from 10 to 18 % by weight of the elastomer particles or elastomer particle aggregates, expressed in terms of the mass of the syrup.

20 4. Moulding composition according to ^{claim 1} ~~one of Claims 1 to 3~~, characterised in that the elastomer of the particles or aggregates consists of partially crosslinked polymer.

25 5. Moulding composition according to ^{claim 1} ~~one of the preceding claims~~, characterised in that the elastomer particles have a core/shell structure, the core being formed by an elastomer and the shell from a matrix-compatible polymer which is essentially insoluble in the syrup.

30 6. Moulding composition according to Claim 5, characterised in that the shell is chemically bonded to the core elastomer.

008760" 7429960

20-1-52

1a

1a

1a

7. Moulding composition according to Claim 5 ~~or 6~~, characterised in that the shell comprises a thermoplastic polymer.

8. Moulding composition according to Claim 5 ~~or 6~~, characterised in that the shell comprises a partially crosslinked polymer.

9. Moulding composition according to ^{claim 5} ~~one of Claims 5 to 8~~, characterised in that the shell is swellable in the syrup of the moulding composition.

10. Moulding composition according to ^{claim 5} ~~one of Claims 5 to 9~~, characterised in that the shell comprises an acrylate polymer.

11. Moulding composition according to ^{claim 1} ~~one of the preceding claims~~, characterised in that the core consists of a partially crosslinked polysiloxane, which is grafted with an acrylate monomer to form the shell.

12. Moulding composition according to ^{claim 5} ~~one of Claims 5 to 11~~, characterised in that the proportion by weight of the core in the core/shell elastomer particles amounts to a proportion of from 40 to 60 % by weight.

13. Moulding composition according to ^{claim 1} ~~one of the preceding claims~~, characterised in that the filler content is from 60 to 80 % by weight, expressed in terms of the moulding composition.

14. Sanitary-ware component, produced using a moulding composition according to ^{claim 1} ~~one of Claims 1 to 13~~.

15. Sanitary-ware component in the form of a kitchen sink according to claim 14, the bottom thickness of the kitchen sink being less than 7 mm.

16. Kitchen sink according to Claim 15, characterised in that the bottom thickness is ≤ 5 mm.